

Lightweight latex gloves that provide superior comfort and tactility

- **Exceptional fit and feel:** Made from high-quality elastic latex, TouchNTuff® 69-318 gloves offer superior comfort
- **Heightened sensitivity:** The thin design provides excellent tactility when compared to standard latex gloves
- **Secure handling:** Textured fingers for easy handling of small objects and delicate instruments
- **Food handling compliance:** These gloves are food-handling compliant, and thus are suitable for a wide variety of food handling applications



CAUTION: This product contains natural rubber latex, which may cause allergic reactions

Industries

- Life Sciences
- Food Processing
- Chemical

Recommended For

- Sample taking and processing
- Testing
- Vehicle maintenance
- Food contact
- All food processing, applications that have food contact
- Food processing and handling
- Meat, Fish and Food Processing
- Secondary food processing

TECHNICAL DATA SHEET

| Product Information | |
|-------------------------------------|--|
| External Glove Surface | Fully Textured |
| Audit Standards | ISO 13485, ISO 9001 |
| Product Certification | Category III, EN ISO 21420:2020, EN ISO 374-1:2016 Type B KPT, EN ISO 374-5:2016 Virus, FDA21 CFR 177-2600-US Food Contact Approved, EU Food Contact Approved, ISO 13485, ISO 9001, UKCA |
| Packaging Overview | 100 gloves per dispenser 10 dispensers per case 1000 gloves per case |
| Storage Instructions | Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition. |
| Country Of Origin | Malaysia |
| Product Segmentation | Multi-Purpose |
| Antistatic | Not Tested |
| Silicone Free | Yes |
| Vulcanization Chemical Accelerators | <ul style="list-style-type: none"> Zinc Diethyldithiocarbamate (ZDEC) Zinc Dibutyldithiocarbamate (ZDBC) Natural rubber proteins <p><i>Only a very small number of users may be sensitive to this ingredient(s) and hence may develop irritant and/or allergic contact reactions.</i></p> |

PHYSICAL PROPERTIES

| | Typical Values | | Testing Method |
|---|---------------------|--------------------|----------------------|
| Length (mm/inches) | 240 / 9.5 | | ASTM D3767, EN 420 |
| Freedom from Holes (Inspection level I) | 1.5 AQL | | ASTM D5151, EN 455-1 |
| Palm Thickness (mm/mils) | 0.12/ 4.7 | | ASTM D3767, EN 420 |
| Finger Thickness (mm/mils) | 0.14 / 5.5 | | ASTM D3767, EN 420 |
| | BEFORE AGING | AFTER AGING | |
| Ultimate Tensile Strength (MPa) | ≥ 18 | ≥ 14 | ASTM D412 & D573 |
| Elongation at Break (%) | ≥ 650 | ≥ 500 | ASTM D412 |

ORDERING INFORMATION

| Size | XS (5.5 - 6) | S (6.5 - 7) | M (7.5 - 8) | L (8.5 - 9) | XL (9.5 - 10) |
|--------------|--------------|-------------|-------------|-------------|---------------|
| Product Code | 69318060 | 69318070 | 69318080 | 69318090 | 69318100 |

Performance Standards and Regulatory Compliance



For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV
T: +32 (0) 2 528 74 00
F: +32 (0) 2 528 74 01

Asia Pacific Region

MY +603 8310 6688
apac.medical@ansell.com
CN: +86 21 38275000
infochina@ansell.com
JP: +813 5549 8151
info.medical.jp@ansell.com

North America Region

Ansell Healthcare Products LLC
T: +1 800 800 0444
F: +1 800 800 0445

Latin America & Caribbean Region

BR +55 (11) 3356-3100
latam.medical@ansell.com
MX: +52 442 296 2050
latam.medical@ansell.com
CO: +57 1 288 3247
latam.medical@ansell.com

Australia

Ansell Limited
T: +61 1800 337 041
F: +61 1800 803 578

Russia

Ansell PYC
Ten. +7 495 258 13 16

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending; www.ansell.com/patentmarking © 2025 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

